

MAINTENANCE SHEET

MAINTENANCE VARNISHED WOODEN FLOORS



IN GENERAL

During the first 7 days the varnish hardens (especially two-component varnish). Therefore Following precautions are recommended:

- Don't move heavy furniture or seats (drag).
- Dust with a vacuum, broom or cloth (not impregnated materials).
- Apply adequate protection (felt) under the legs of tables and chairs.

MAINTENANCE

The varnished floor must be cleaned with a vacuum cleaner and Hardfloor Ciranova Fresh®. Please note that you don't use products that contain waxes because this can cause adhesion problems for the after-treatment. Then maintain with Hard Floor Polish Ciranova®.

REGULAR MAINTENANCE

Regular maintenance with Hard floor Fresh Ciranova®, a water-based ecological cleaner for all types varnished or lacquered wooden floors. Mix 100ml in 10l lukewarm water. Moisten the cloth with this solution and mop the floor fresh and hygienic at once. Rinse out the mop and wring out well. Avoid excess moisture on the wooden floor.

AFTER TREATMENT

Prevent early wear to the surface by using Hard Floor Polish Ciranova®. With new varnished floors, you need to wait at least 14 days before you use the polish. Pour a little bit of Hardfloor Polish Ciranova® on the floor and spread it with even strokes over the surface with a mop. Always mop in the direction of the wood to avoid streaks. It is advisable to use Hardfloor Polish Ciranova® 4 times a year in commercial spaces etc., and use Hard Floor Cleaner to remove old contaminated layers.

RENOVATION

To renovate a varnished wooden floor, you first need to sand the old layers of varnish, remove the sanding dust and then you must apply a new coat(s) of varnish. On a lacquered wooden floor, the wood will fade where the varnish is worn what makes it difficult to obtain a uniform finish. Therefore it is important to apply timely a new coat of varnish (after completely sanded the old layers). After finishing the wooden floor, respect the time needed so the varnish can hard out.



Ciranova® products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

Produced by Debal Coatings nv

Industrieweg 29 – B 8800 Beveren-Roeselare
tel. +32 (0) 51 30 11 40 fax +32 (0) 51 31 26 48
www.ciranova.be ciranova@ciranova.be